

11/01/01



J0663 U.S. PTO

12-06-01

10004385 11/01/01

## PATENT APPLICATION TRANSMITTAL LETTER

(Large Entity)

Docket No.

56232.10 [4874]

TO THE COMMISSIONER FOR PATENTS

Transmitted herewith for filing under 35 U.S.C. 111 and 37 C.F.R. 1.53 is the patent application of:

SHIMIZU, Kunio; KOBAYASHI, Toru

For: Protective Film Of A Polarizing Plate

Enclosed are:

- ☒ Certificate of Mailing with Express Mail Mailing Label No. EL852371030US  
☐ Sheet(s) of Informal/Formal drawing  
☒ Assignment including Form PTO-1595.  
☒ Declaration ☒ Signed ☐ Unsigned.  
☒ Power of Attorney  
☐ Information Disclosure Statement  
☐ Preliminary Amendment  
☒ Other: Certified Copy of Japanese Appln. No. 2000-338883 -

J1000 U.S. PTO  
10/004385  
11/01/01

## CLAIMS AS FILED

For	#Filed	#Allowed	#Extra	Rate	Fee
Total Claims	17	- 20 =	0	x \$18.00	\$0.00
Indep. Claims	2	- 3 =	0	x \$80.00	\$0.00
Multiple Dependent Claims (check if applicable) <input type="checkbox"/>					\$0.00
BASIC FEE					\$740.00
TOTAL FILING FEE					\$740.00

- ☒ A check in the amount of \$740.00 to cover the filing fee is enclosed.  
☒ The Commissioner is hereby authorized to charge and credit Deposit Account No. 07-1850 as described below. A duplicate copy of this sheet is enclosed.  
☐ Charge the amount of \$\_\_\_\_\_ as filing fee.  
☒ Credit any overpayment.  
☒ Charge any additional filing fees required under 37 C.F.R. 1.16 and 1.17.  
☐ Charge the issue fee set in 37 C.F.R. 1.18 at the mailing of the Notice of Allowance, pursuant to 37 C.F.R. 1.311(b).

Dated: November 1, 2001

  
Signature

## **PROTECTIVE FILM OF A POLARIZING PLATE**

### **FIELD OF THE INVENTION**

The present invention relates to a protective film of a polarizing plate used for a liquid crystal display having superior dimension stability, and particularly to a polymer-containing protective film of a polarizing plate.

### **BACKGROUND OF THE INVENTION**

A cellulose triacetate film has been used conventionally as a base film of silver halide photographic light sensitive materials. The cellulose triacetate film has also been applied to a protective film of a polarizing plate, but an additional property which is not required in silver halide photographic light sensitive materials is required for its use in the protective film. A plasticizer is contained in a cellulose acetate film used for a protective film of a polarizing plate, as in silver halide photographic light

sensitive materials, for the purpose of providing flexibility and hydrophobicity to the film.

In recent years, developments have been made regarding to thinner and light-weight information processing apparatus equipped with a liquid crystal display, such as notebook personal computers, car navigation systems, cell phones and game devices. Requirements for a thinner protective film of a polarizing plate used in a liquid crystal display have become stronger in response to the above-mentioned trend. Therefore, the protective film of a polarizing plate tends to be made extremely thinner, compared to the base film for light sensitive silver halide photographic materials. A decrease of a film thickness results in lowered moisture-resistance, lowering performance of a liquid crystal display in high humidity, specifically under environments of high temperature and humidity.

Further, during the drying process after casting of the film, plasticizers may migrate in the thickness direction of the film web, resulting in inhomogeneous distribution of the plasticizer, and the plasticizer may bleed out onto the web surface, or may be evaporated or vaporized to condense and be accumulated on the wall of the film-forming apparatus, forming liquid drops which contaminates the web or rolls. Simply decreasing a cellulose triacetate film thickness

deteriorates moisture-resistance, leading to insufficient shield against moisture and deteriorating a polarizer or an adhesive used to adhere the polarizer to the cellulose triacetate film, after an assembly of a polarizing plate. To overcome such a problem, there appeared a proposal to increase the plasticizer in order to compensate for the decrease in film thickness. However, it was proved that a simple increase of the plasticizer accelerated bleeding-out of a plasticizer onto the surface of cellulose film and there took place a new problem in addition to those arising with silver halide photographic light sensitive materials. Additives such as a plasticizer often bleed out or evaporate out of the film under environments of high temperature and high humidity to reduce the weight of the film. The property that such additives are retained within the film is called retainability. Such retainability of conventional cellulose acetate films is poor, causing deterioration of performance of a liquid crystal display device.

An increase of a plasticizer further lowers the glass transition temperature (also denoted as  $T_g$ ) of a cellulose triacetate film, producing problems such that softening the cellulose triacetate film deteriorated dimensional stability (including shrinkage ratio, coefficient of hygroscopic expansion and coefficient of thermal expansion) of the film.

To overcome the foregoing problems, a technique is disclosed, in which a polymer such as polyester, polyester ether, or polyurethane ether, is incorporated as a polymer plasticizer, optionally in combination with a low molecular weight plasticizer, as described, for example, in JP-B 47-760, 43-1635 (the term, JP-B refers to examined and published Japanese Patent), JP-A 5-197073 (the term, JP-A refers to unexamined and published Japanese Patent Application), and U.S. Patent 3054673, 3277031. Further, a technique is also proposed, in which an acryl-type polymer or a polymer obtained by causing an acryl-type monomer to polymerize in the presence of cellulose triacetate is incorporated in a cellulose triacetate film. However, there arose problems that a polymer plasticizer caused phase separation between cellulose triacetate and the polymer in a cellulose triacetate dope, in the web during the drying process or after film formation, resulting in deteriorated transparency, increased water permeability, inhomogeneous shrinkage or lowered shrinkage rate of the film.

A first object of the present invention is to provide a cellulose ester film as a protective film of a polarizing plate which does not contaminate films or equipment because of elution, evaporation or vaporization of low molecular

weight additives such as a plasticizer during the film production.

A second object of the present invention is to provide a cellulose ester film as a protective film of a polarizing plate exhibiting superior moisture-resistance, without deteriorating a polarizer even under the condition of high temperature or of high temperature and high humidity.

#### SUMMARY OF THE INVENTION

The above objects can be accomplished by each of the following constitutions.

1. A protective film of a polarizing plate comprising a cellulose ester film, wherein a variation in a weight of the cellulose ester film is 0 to 2% under a keeping condition of  $80 \pm 5$  °C and  $90 \pm 10\%$  RH for 48 hours.
2. The protective film of a polarizing plate of item 1, wherein the cellulose ester film contains a plasticizer in an amount of 1 to 30 weight % of the cellulose ester film.
3. The protective film of a polarizing plate of item 1, wherein a moisture permeability of the cellulose ester film is 50 to 250 g/m<sup>2</sup>·24hr and a thickness of the cellulose ester film is 10 to 60 μm.
4. A protective film of a polarizing plate comprising a cellulose ester film, wherein the cellulose ester film

5. The protective film of a polarizing plate of item 4, wherein the plasticizer is rosin or a rosin derivative.

6. The protective film of a polarizing plate of item 5, wherein the plasticizer is hydrogenated and has an acid value of 100 to 250.

7. The protective film of a polarizing plate of item 4, wherein the plasticizer is an epoxy resin.

8. The protective film of a polarizing plate of item 7, wherein the plasticizer is a phenol-novolac epoxy resin or a cresol-novolac epoxy resin.

9. The protective film of a polarizing plate of item 4, wherein the plasticizer is a ketone resin.

10. The protective film of a polarizing plate of item 4, wherein the plasticizer is a *p*-toluenesulfonamide resin.

11. The protective film of a polarizing plate of item 4, wherein a variation in a weight of the cellulose ester film is 0 to 2% under a keeping condition of  $80 \pm 5$  °C and  $90 \pm 10\%$  RH for 48 hours.

12. The protective film of a polarizing plate of item 1,

wherein the cellulose ester film contains a plasticizer selected from the group consisting of rosin and rosin derivatives.

13. The protective film of a polarizing plate of item 12, wherein the plasticizer is hydrogenated and has an acid value of 100 to 250.

14. The protective film of a polarizing plate of item 1, wherein the cellulose ester film contains a plasticizer selected from epoxy resins.

15. The protective film of a polarizing plate of item 14, wherein the plasticizer is a phenol-novolac epoxy resin or a cresol-novolac epoxy resin.

16. The protective film of a polarizing plate of item 1, wherein the cellulose ester film contains a plasticizer selected from ketone resins.

17. The protective film of a polarizing plate of item 11, wherein the cellulose ester film contains a plasticizer selected from p-toluenesulfonamide resins.

#### DETAILED DESCRIPTION OF THE INVENTION

The present invention is further detailed as below.  
A cellulose triacetate film has been applied to a protective film of a polarizing plate because of its good transparency, free of optical strain (low retardation) and




excellent adhesion to a polarizer. It is common practice that a plasticizer is incorporated into the protective film of a polarizing plate in order to protect the polarizer layer and make a polarizer layer easier to be processed. Examples of plasticizers preferably incorporated are; phosphates such as, triphenyl phosphate, tricresyl phosphate, cresyl diphenyl phosphate, octyl diphenyl phosphate, diphenyl biphenyl phosphate, trioctyl phosphate and tributyl phosphate; phthalates such as diethyl phthalate, dimethoxyethyl phthalate, dimethyl phthalate, dioctyl phthalate, dibutyl phthalate and di-2-ethylhexyl phthalate; glycolates such as triacetin, tributyrin, butylphthalylbutyl glycolate, ethylphthalylethyl glycolate, methylphthalylethyl glycolate and butylphthalylbutyl glycolate. However, there was a problem that a plasticizer tended to precipitate by vaporization of a solvent during the casting process due to poor miscibility with cellulose ester.

A plasticizer, which has a relatively low molecular weight, exhibiting a low boiling point, easily bled out during the drying stage of the production process and proved to be providing a main cause of contamination of production equipments.


A cellulose triacetate film has insufficient moisture-resistance, particularly poor moisture-resistance in thin films (not more than 60  $\mu$ m).

According to the present invention, it was found that the foregoing problems were solved by using rosin resin, epoxy resin, ketone resin and *p*-toluenesulfonamide resin as a plasticizer.

Examples of cellulose esters according to the invention are; cellulose triacetate, cellulose diacetate, cellulose acetate butyrate, cellulose acetate propionate and cellulose acetate propionate butyrate. As for cellulose triacetate, it is preferred to have a degree of polymerization of 250 to 400 and an acetic acid content of 54 to 62.5%, and more preferably 58 to 62.5% in terms of mechanical strength. Cellulose triacetate synthesized from cotton linter and that synthesized from wood pulp can be used each alone or in combination. It is more preferred to use cellulose triacetate synthesized from cotton linter, which exhibits superior peelability from a drum or belt, in terms of higher production efficiency. It is preferable to use cellulose triacetate synthesized from cotton linter at a ratio of not less than 60% by weight, and more preferably not less than 85% by weight, and it is still more preferable to use alone, in terms of the marked effect on the peelability.





## Parastoric acid



KE-604


KE-610



Of these compounds, KE-604 and KE-610 are commercially available from Arakawa Kagaku Kogyo Co. Ltd., having acid values of 237 and 170, respectively. KE-100 and KE-356, which are esterification products of three-stuff mixtures of abietic acid, dehydroabietic acid and parastoric acid, are also commercially available from Arakawa Kagaku Kogyo Co. Ltd., as of acid values of 8 and 0 respectively. Mixtures of abietic acid, dehydroabietic acid and parastoric acid, are also available from Harima Kasei Co. Ltd., as G-7 and HARTALL R-X whose acid values are 167 and 168, respectively.


Epoxy resins include those of the following structures.

Araldite EPN1179



molecular weight: ca.405


Araldite AER260




Araldite EPN1179 and Araldite AER260 are commercially available from Asahi Ciba Co., Ltd.

Ketone resin includes those of the following structures.

Hilac 110




Hilac 110H



Hilac 110 and Hilac 110H are commercially available from Hitachi Kasei Co., Ltd.

*p*-toluenesulfonamide resins include those of the following structures and are also commercially available as Toplr from Fuji Amido Chemicals Co., Ltd.

Toplr



$$n = 2 \text{ to } 4$$

The proportion of solvents usable in the invention is preferably at 88 to 96% by weight of methylene chloride and 4 to 12 % of other solvent(s), and more preferably at 90 to 94% by weight of methylene chloride and 6 to 10% of other solvent(s).

Further, the concentration of a cellulose ester plus a plasticizer, based on the total amount of dope is preferably 15 to 30 % by weight, and more preferably 18 to 25 % by weight. The concentration of a cellulose ester plus the foregoing polymer is preferably 15 to 30 % by weight, and more preferably 18 to 25 % by weight, based on the total amount of dope.

The temperature of the heating dissolution with adding a solvent is preferably over the boiling point of the solvent used and within the temperature range of causing no boiling. The temperature is preferably set, for example, to not lower than 60 °C and more preferably in the range of 80 to 110 °C. Pressure is set so that the solvent does not boil at the thus set temperature.

After completing dissolution, a dope is taken out of a vessel, while cooling, or discharged by a pump out of the vessel, followed by cooling through a heat-exchanger, to be fed to the casting process.

The preparation method of a cellulose ester film used in the invention is not specifically limited and several methods commonly known in the art are applicable, as described in U.S. Patent 2492978, 2739070, 2739069, 2492977, 2336310, 2367603 and 2607704; British Patent 64071 and



The dope may be cooled to room temperature, but more preferably to a temperature by 5 to 10° C lower than the boiling point and fed to the casting process while keeping the temperature so that the viscosity of the dope can be lowered.

According to the invention, a dope prepared by dissolving a cellulose ester is cast onto a support (casting process); a part of the solvent is removed by heating (drying-on-support process); the film is peeled off from the support; and the peeled film is dried (film drying process) to obtain a cellulose ester film.

As a support used in the casting process is used a belt-form or drum-form, mirror-polished stainless steel support. Casting can be performed while the support is generally maintained within a temperature higher than 0 °C and lower than the boiling point of the solvent, in the casting process, casting onto the support at a temperature of 5 to 15° C is more preferred, thereby gelling the dope and shortening the limiting peel-off time. The limiting peel-off time means the time duration when the cast dope stays on a support at the critical casting speed at which transparent and very flat film is continuously obtainable. To enhance production efficiency, a shorter limiting peel-off time is preferable.

In the process of drying a film on a support, after a dope is cast and gelled, the dope is maintained preferably at a temperature of 40 to 70 °C, and more preferably at 55 to 70° C within a time of 30% from the casting, based on the time duration from casting to peeling being 100%. Thereby,

evaporation of the solvent is accelerated, enabling a film to be peeled from a support much faster and also increasing the peel strength of the film. This temperature is preferably maintained for a period of not less than 20%, and more preferably not less than 40%. The film is preferably peeled from the support in the drying process when the amount of residual solvent is 30 to 150%, more preferably 40 to 120%, and still more preferably 80 to 100%, thereby lowering the strength of peeling-off from the support. The temperature at which the dope is peeled from a support is preferably 0 to 30° C, and more preferably 5 to 20° C to increase the base film strength and prevent tear-off of the base.

The residual solvent amount is defined according to the following equation:

Residual solvent amount

$$= \{ (\text{Residual volatile matter weight}) / (\text{film weight after subjected to thermal treatment}) \} \times 100(\%),$$

wherein the residual volatile matter weight means the value equal to a film weight before being subjected to thermal treatment at 115 °C for 1 hr minus the film weight after being subjected to the thermal treatment.

In the film drying process, the film peeled from the support is further dried to lower the residual solvent amount to not more than 5% by weight, preferably not more than 2% by

weight, and more preferably not more than 0.5% by weight, in order to obtain a film exhibiting superior dimensional stability. In the film drying process, the film is dried while being transported by means of a roll-hanger method, a pin-tenter method or a clip-tenter method. For use as a liquid crystal display member, a film is preferably dried with maintaining the film width by the tenter method to enhance dimension stability. Specifically preferable is keeping the film width while the film contains a relatively large amount of residual solvent immediately after peeled from the support, to display an enhanced effect of dimensional stability.

The film tends to shrink in the width direction by evaporation of a solvent specifically in the drying process after having been peeled from the support. Drying at a higher temperature results in greater shrinkage. It is preferred to perform drying with minimal shrinkage in the drying process to achieve superior film flatness. In this regard, the tenter method is preferred, in which the film is dried in whole or a part of the drying process, while maintaining its width by holding both width edges of the film with clips, such as described in JP-A 62-46625.

Means for drying the film are not specifically limited and there are generally utilized hot air, infrared radiation,

The thickness of the cellulose ester film according to the invention is preferably 10 to 60  $\mu\text{m}$ , and more preferably 30 to 50  $\mu\text{m}$ , in terms of demand for a thin-walled and lightweight polarizing plate used in the liquid crystal display. When the thickness is less than this, troubles tend occur, caused by generation of wrinkle and the like wrinkle in the process of preparing the liquid crystal display, while the

thickness more than this results in little contribution to the liquid crystal display.

The cellulose ester film according to the invention, after being aged at 80° C and 90% RH for 50 hrs. preferably exhibits a dimensional stability in both longitudinal and transverse directions of -0.5 to +0.5%, and more preferably -0.4 to +0.4%, and still more preferably -0.3 to +0.3%.

The cellulose ester film preferably exhibits a curl value of -20 to +40 (in 1/m), and more preferably -20 to +35, and still more preferably -20 to +25 at 23 °C and 80% RH.

The cellulose ester film preferably exhibits a curl value in 40 °C water of -20 to +60 (in 1/m), and more preferably -20 to +50, and still more preferably -20 to +40.

To a cellulose ester film according to the invention, fine particles such as silicon oxide as a matting agent may optionally be incorporated. The fine particles such as silicon oxide are preferably subjected to a surface treatment by an organic compound to minimize haze of the film. Preferred organic compounds used for the surface treatment include, for example, halosilanes, alkoxysilanes, silazane, and siloxane. The average primary particle size is preferably 5 to 50 nm and more preferably 7 to 14 nm since the larger the average particle size, the greater the matting effect, while the smaller the average particle size, the

better the transparency. Examples of fine particles of silicone oxide include AEROSIL 200, 200V, 300, R972, R974, R202, R812, OX50 and TT600, which are produced by Aerosil Co. Ltd., of which AEROSIL 200V, R972, R974, R202 and R812 are preferable.

The cellulose ester film according to the invention preferably contains minimal foreign matter. It is specifically preferred to contain foreign matter detectable under the polarizing crossed-Nicols condition, in a less amount. The foreign matter detectable under the polarizing crossed-Nicols condition means that determined by placing a cellulose ester film between two sheets of polarizer which are arranged vertical to each other (crossed-Nicols condition). Such foreign matter under the polarizing crossed-Nicols condition is observable in a dark visual field as a lightened spot only where the foreign matter exists, so that the size and number are easily recognized. The number of foreign matter particles observed in an area of 250 mm<sup>2</sup> under the polarizing crossed-Nicols condition is preferably not more than 200 for a particle size of 5 to 50  $\mu$ m and zero for a particle size of larger than 50  $\mu$ m, more preferably not more than 100 for a particle size of 5 to 50  $\mu$ m, and still

more preferably not more than 50 for a particle size of 5 to 50  $\mu\text{m}$ .

The preparation method for the above-described cellulose ester film containing less foreign matter is not specifically limited and may be accomplished by filtering a dope compositions obtained by dissolving the cellulose ester in a solvent, using the following filter paper. It is preferred to use a filter paper having a water filtration time (based on JIS P3801 7.5) of not less than 20 sec. and to perform filtration of a dope for casting under a filtering pressure of not more than 16  $\text{kg}/\text{cm}^2$ . More preferred is to use a filter paper of less than 30 sec. under a filtering pressure of not more than 12  $\text{kg}/\text{cm}^2$ , and still more preferred is to use a filter paper of not less than 40 sec. under a filtering pressure of not more than 10  $\text{kg}/\text{cm}^2$ . Further, the foregoing filter paper is preferably used by layering two or more sheets. The filtering pressure is controllable by optimally selecting a filtration flow amount and filtration area.

The cellulose ester film according to the invention can be used as a member for use in liquid crystal display. The member for use in the liquid crystal display means material which is used in the liquid crystal displaying device and includes a polarizing plate, protective film of a polarizing



The preparation method of a polarizing plate according to the invention is not specifically limited and it can be prepared by any general method. There is, for example, a method in which a cellulose triacetate film is treated with alkali and is laminated by use of an aqueous solution of completely saponified polyvinyl alcohol onto both surfaces of a polarizer film made by being dipped and stretched in an iodine solution. Instead of the alkali-treatment, such methods to enhance adhesion, as described in JP-A 6-94915 and 6-118232, may be applied.

## Examples

The present invention will be further explained based on examples, but the invention is not limited to these examples.

### Example 1

## Dope composition:

Triacetyl cellulose (acetic acid content: 61.0%)	100 parts by weight
2-(2'-Hydroxy-3',5'-di-t-butylphenyl) benzotriazole	1 part by weight
Additive described in Table 1	20 parts by weight
Methylene chloride	475 parts by weight
Ethanol	50 parts by weight

The dope compositions were charged in a closed vessel, heated up to 70° C, and cellulose triacetate (TAC) was completely dissolved with stirring to obtain a dope. The time required for dissolution was 4 hrs. The dope compositions were filtered and the dope maintained at 35° C was uniformly cast on a support of stainless steel band kept at 30° C.

Then, the dope was peeled off from the stainless band support after it was dried to such an extent as being peelable. Residual solvent in the dope was 25% at this time. The period of time required for casting to peeling of the dope was 3 min. After peeled from a stainless support, the film was dried at 120 °C while being held in the transverse direction. Then, the transverse holding was released and drying was completed in a drying zone of 120 to 135 °C, while being transported by a number of rolls. The film was

Triacetyl cellulose (acetic acid  
content: 61.0%) 100 parts by weight

2-(2'-Hydroxy-3',5'-di-t-butylphenyl) benzotriazole	1 part by weight
Triphenylphosphate	20 parts by weight
Methylene chloride	475 parts by weight
Ethanol	50 parts by weight

The dope solution of the above composition was prepared according to a method well-known in the art, filtered, and then uniformly cast at a dope temperature of 35 °C onto a support kept at 30 °C. Casting onto the support was performed so that the dry film thickness was 60  $\mu$ m.

Then, the dope was peeled off after being dried to an extent of being peelable, and further dried at 120° C for 10 min. Thus obtained film was<sup>o</sup> provided with a knurling of 10 mm in width and 5  $\mu$ m in height on both sides of the film to prepare film samples Nos. 12 and 13 with a thickness of 60 and 40  $\mu$ m respectively. The film width was 1300 mm and the wound-up length was 2000 m.

#### Comparative Example 2

A film sample No. 14 having a film thickness of 60  $\mu$ m was prepared by casting in a manner similar to foregoing Comparative Example 1, except that the dope composition was varied, as shown below.

Dope composition:

Triacetyl cellulose (acetic acid content: 61.0%)	100 parts by weight
2-(2'-Hydroxy-3',5'-di-t-butylphenyl) benzotriazole	1 part by weight
Ethylphalylethyl glycolate	20 parts by weight
Methylene chloride	475 parts by weight
Ethanol	50 parts by weight

Comparative Example 3

A film sample No. 15 having a film thickness of 60  $\mu$ m was prepared by casting in a manner similar to the foregoing Comparative Example 1, except that the dope composition was varied, as shown below.

Dope composition:

Triacetyl cellulose (acetic acid content: 61.0%)	100 parts by weight
2-(2'-Hydroxy-3',5'-di-t-butylphenyl) benzotriazole	1 part by weight
Butylbenzyl phthalate	20 parts by weight
Methylene chloride	475 parts by weight
Ethanol	50 parts by weight

Comparative Example 4


A film sample No. 16 having a film thickness of 60  $\mu$ m was prepared by casting in a similar manner to the foregoing

Comparative Example 1, except that the dope composition was varied, as shown below.

Dope composition:

Triacetyl cellulose (acetic acid content: 61.0%)	100 parts by weight
2-(2'-Hydroxy-3',5'-di-t-butylphenyl) benzotriazole	1 part by weight
Compound described in JP-A 60-25053 (having structure (A) shown below)	20 parts by weight
Methylene chloride	475 parts by weight
Ethanol	50 parts by weight

(A)



#### Preparation of Comparative Polarizing Plate Sample

Film samples Nos. 12 to 16 of Comparative Examples were subjected to a saponification treatment in a manner similar to that of Example 1 to prepare polarizing plates.

The thus prepared film samples Nos. 1 to 16 and polarizing plate samples Nos. 1 to 16 were evaluated with respect to performance in the following manner.

Evaluation method:

Evaluation of Retainability:

### Measurement of Moisture Permeability

Moisture permeability of each sample was measured according to the method described in JIS Z 0208.

#### Dimensional Stability

Cross patterns were marked at two points (Machine Directions (MD) and longitudinal directions) on the surface of film samples, and samples were subjected to a thermal treatment (at 80° C, 90% RH, 50 hrs.), after which the distance between the marks was measured by an optical microscope.

Dimensional stability was determined according to the following equation, where  $a_1$  is the distance before being subjected to the thermal treatment and  $a_2$  is the distance after being subjected to the thermal treatment:

$$\text{Dimensional stability (\%)} = [(a_1 - a_2) / a_1] \times 100$$

#### Durability Test of Polarizing Plate

Two sheets of 10 cm x 10 cm polarizing plate sample were subjected to a thermal treatment (at 80 °C, 90% RH, for 50 hrs.), and the length of a white border portion around the longer center line in the longitudinal or transverse directions, when the two sheets were superposed at a right angle, was measured to determine the levels as described below. The white border portion means the state that light passes through at a border part of a polarizing plate where



light should essentially not pass through when two polarizing plates were placed at a right angle to each other, and it can be visually judged. In a polarizing plate, this causes a defect which makes the displayed image at the border invisible. The results of evaluation according to the following criteria are shown in Table 1.

- A: the white border portion is less than 5% (a level causing no problem as a polarizing plate),
- B: the white border portion is not less than 5% and less than 10% (a level causing no problem as a polarizing plate),
- C: the white border portion is not less than 10% and less than 20% (a level barely usable as a polarizing plate),
- D: the white border portion is not less than 20% and less than 50% (a level causing a problem as a polarizing plate),
- E: the white border portion is not less than 50% (a level not usable as a polarizing plate).

Rank C and better ranks are levels acceptable for practical use.

Table 1

Film Sample No.	Additive	Film thickness (µm)	Retainability (weight %)		Moisture Permeability g/m <sup>2</sup> . 24hr	Dimensional Stability (%)		Durability of Polarizing Plate	Note
			140°C, 10 min.	80°C, 90% 48hr		Longitudinal Direction	Lateral Direction		
1	Rosin (KE-604)	60	0.0	0.4	211	-0.06	-0.03	A	Inv.
2	Rosin (KR-610)	40	0.0	0.5	242	-0.07	-0.05	A	Inv.
3	Rosin (KE-100)	60	0.1	0.6	230	-0.10	-0.08	A	Inv.
4	Rosin (KE-356)	60	0.1	0.3	203	-0.06	-0.05	A	Inv.
5	Rosin (G-7)	60	0.2	0.7	245	-0.09	-0.11	A	Inv.
6	Rosin (R-X)	60	0.1	0.7	236	-0.07	-0.05	A	Inv.
7	Epoxy (EPN1179)	60	0.1	0.7	198	-0.07	-0.03	A	Inv.
8	Epoxy (AER260)	60	0.0	0.7	205	-0.17	-0.13	A	Inv.
9	Keton (Hilac 111)	60	0.2	0.9	248	-0.08	-0.03	A	Inv.
10	Keton (Hilac 110H)	60	0.1	0.5	240	-0.07	-0.03	A	Inv.
11	Paratoluenesulphonamide (Topler)	60	0.3	1.5	210	-0.77	-0.53	B	Inv.
12	Triphenylphosphate	60	1.3	5.5	280	-1.22	-1.11	E	Comp.
13	Triphenylphosphate	40	1.5	6.7	310	-1.30	-1.06	E	Comp.
14	Ethyl phthalilethyl glycolate	60	1.2	4.0	290	-1.34	-1.44	D	Comp.
15	Butyl benzyl phthalate	60	2.0	8.3	330	-2.01	-1.81	E	Comp.
16	Compound A	60	0.2	5.9	350	-1.01	-0.91	D	Comp.

Inv.: Invention, Comp.: Comparison

As can be seen from Table 1, according to the invention, foreign matter, which is the cause of defects in a cellulose ester film used as a protective film of a polarizing plate, were minimized in number and durability of a polarizing plate itself was not lowered.